



TEXFILTRA, S.L.  
C.I.F. B60 198 546  
C/Costa i Déu núm. 63  
08205 Sabadell  
Barcelona (España)



Tel. 34 93 712 34 27 Fax. 34 93 720 80 00  
[Info@texfiltra.es](mailto:Info@texfiltra.es)  
[www.texfiltra.es](http://www.texfiltra.es)

# Ref. 5200-F-ANT

Fabric Width (cm) 170

## Technical Specifications

Permeability (DIN-53887:1986) [liters/dm <sup>2</sup> /min a 20mmwg (±20%)]	<b>160</b>
---	------------

## Characteristics

Composition	<b>Polyester Food + Bekinox®</b>
Weave	<b>Satin</b>
Weight (ISO-3801-1977) [g/m <sup>2</sup> ]	<b>180</b>
Thickness (EN-ISO-5084-1997) [mm]	<b>0,3</b>
Warp Composition	<b>Multifilament + Bekinox®</b>
Weft Composition	<b>Multifilament + Bekinox®</b>
Warp Density [Threads/cm]	<b>117</b>
Weft Density [Threads/cm]	<b>45</b>
Vertical Strength 5cm (EN-ISO-13934-1:1999) [kg - N]	<b>150 - 1500</b>
Horizontal Strength 5cm (EN-ISO-13934-1:1999) [kg - N]	<b>58 - 580</b>
Warp Electrical Surface Resistance (DIN-54345:1985 part5) [MOhms]	<b>&lt;1.0</b>
Weft Electrical Surface Resistance (DIN-54345:1985 part5) [MOhms]	<b>&lt;1.0</b>
Particle Retention Capacity (TEXMAX-60255) [Ø=a µm]	<b>25</b>
Finish	<b>Heat Set</b>

Revision 01/02/2016