



TEXFILTRA, S.L.
C.I.F. B60 198 546
C/Costa i Déu núm. 63
08205 Sabadell
Barcelona (España)



Tel. 34 93 712 34 27 Fax. 34 93 720 80 00
Info@texfiltra.es
www.texfiltra.es

Ref. 7011

Fabric Width (cm) 175

Technical Specifications

Permeability (DIN-53887:1986) [liters/dm ² /min a 20mmwg (±20%)]	8
---	---

Characteristics

Composition	Polypropylene
Weave	Plain
Weight (ISO-3801-1977) [g/m ²]	370
Thickness (EN-ISO-5084-1997) [mm]	0,74
Warp Composition	Multifilament
Weft Composition	Multifilament
Warp Density [Threads/cm]	18
Weft Density [Threads/cm]	10
Vertical Strength 5cm (EN-ISO-13934-1:1999) [kg - N]	360 - 3600
Horizontal Strength 5cm (EN-ISO-13934-1:1999) [kg - N]	220 - 2200
Particle Retention Capacity (TEXMAX-60255) [Ø=a µm]	16,5
Finish	Heat Seat + Calandered

Revision 19/01/2018