



TEXFILTRA, S.L.  
C.I.F. B60 198 546  
C/Costa i Déu núm. 63  
08205 Sabadell  
Barcelona (España)



Tel. 34 93 712 34 27 Fax. 34 93 720 80 00  
[Info@texfiltra.es](mailto:Info@texfiltra.es)  
[www.texfiltra.es](http://www.texfiltra.es)

# Ref. 715-M

## Fabric Width (cm) 140-165-230

### Technical Specifications

Permeability (DIN-53887:1986) [liters/dm <sup>2</sup> /min a 20mmwg (±20%)]	<b>50</b>
---	-----------

### Characteristics

Composition	<b>Polypropylene</b>
Weave	<b>Satin</b>
Weight (ISO-3801-1977) [g/m <sup>2</sup> ]	<b>325</b>
Thickness (EN-ISO-5084-1997) [mm]	<b>0,48</b>
Warp Composition	<b>Monofilament</b>
Weft Composition	<b>Multifilament</b>
Warp Density [Threads/cm]	<b>47</b>
Weft Density [Threads/cm]	<b>13</b>
Vertical Strength 5cm (EN-ISO-13934-1:1999) [kg - N]	<b>300 - 3000</b>
Horizontal Strength 5cm (EN-ISO-13934-1:1999) [kg - N]	<b>280 - 2800</b>
Particle Retention Capacity (TEXMAX-60255) [Ø=a µm]	<b>22,3</b>
Finish	<b>Heat Set + Calendered</b>

Revision 28/11/2017