



TEXFILTRA, S.L.  
C.I.F. B60 198 546  
C/Costa i Déu núm. 63  
08205 Sabadell  
Barcelona (España)



Tel. 34 93 712 34 27 Fax. 34 93 720 80 00  
[Info@texfiltra.es](mailto:Info@texfiltra.es)  
[www.texfiltra.es](http://www.texfiltra.es)

# Ref. 720-M

Fabric Width (cm) 140-165-230

## Technical Specifications

|                                                                             |     |
|-----------------------------------------------------------------------------|-----|
| Permeability (DIN-53887:1986) [liters/dm <sup>2</sup> /min a 20mmwg (±20%)] | 275 |
|-----------------------------------------------------------------------------|-----|

## Characteristics

|                                                        |                       |
|--------------------------------------------------------|-----------------------|
| Composition                                            | Polypropylene         |
| Weave                                                  | Satin                 |
| Weight (ISO-3801-1977) [g/m <sup>2</sup> ]             | 245                   |
| Thickness (EN-ISO-5084-1997) [mm]                      | 0,39                  |
| Warp Composition                                       | Monofilament          |
| Weft Composition                                       | Monofilament          |
| Warp Density [Threads/cm]                              | 45                    |
| Weft Density [Threads/cm]                              | 28                    |
| Vertical Strength 5cm (EN-ISO-13934-1:1999) [kg - N]   | 300 - 3000            |
| Horizontal Strength 5cm (EN-ISO-13934-1:1999) [kg - N] | 200 - 2000            |
| Particle Retention Capacity (TEXMAX-60255) [Ø=a µm]    | 47,2                  |
| Finish                                                 | Heat Set + Calendered |

Revision 05/12/2017