



TEXFILTRA, S.L.
C.I.F. B60 198 546
C/Costa i Déu núm. 63
08205 Sabadell
Barcelona (España)



Tel. 34 93 712 34 27 Fax. 34 93 720 80 00
Info@texfiltra.es
www.texfiltra.es

Ref. 8525

Fabric Width (cm) 200

Technical Specifications

Permeability (DIN-53887:1986) [liters/dm ² /min a 20mmwg (±20%)]	100
---	-----

Characteristics

Composition	Polyester
Weave	Twill
Weight (ISO-3801-1977) [g/m ²]	400
Thickness (EN-ISO-5084-1997) [mm]	0,68
Warp Composition	Staple Fiber
Weft Composition	Staple Fiber
Warp Density [Threads/cm]	22
Weft Density [Threads/cm]	16
Vertical Strength 5cm (EN-ISO-13934-1:1999) [kg - N]	425 - 4250
Horizontal Strength 5cm (EN-ISO-13934-1:1999) [kg - N]	275 - 2750
Particle Retention Capacity (TEXMAX-60255) [Ø=a µm]	66,7
Finish	Heat Set

Revision 21/03/2017